

E-GLASS FIBRE WEBBING - 550°C

Tape is produced by weaving a number of yarns. The width and thickness are determined by the number and thickness of the yarns used.

E-Glass tape is a soft resilient product, available in a number of different thickness' and constructions to provide a comprehensive HT range.

Aladder tapes are also available. This type of webbing has regular perforations in the middle, one-third of the width, to produce a ladder like structure. The webbing can be supplied with self adhesive backing, or with various special coatings.

E-Glass tape is made from texturized, continuous E-Glass fibre filaments up to a maximum of 9 microns. These fibres cause considerably less irritation of the skin than coarser fibres.

Chemical Properties

E-Glass tape exhibits excellent chemical stability resisting attack from most corrosive agents. Exceptions are hydrofluoric acids and phosphoric acids and concentrated alkalis. No water of hydration is present. Excellent die-electrical strength.

Availability

E-Glass tape is available in the following thickness' : 2-5 mm, width 10-200 mm. Other sizes available on request. All E-Glass products are also available in a black version which is made by a colourfast lubricant.

Applications

- Fire-resistant curtains
- Protective clothing
- Controlled cooling of castings
- Insulation of gas and steam turbines
- Welding curtains
- Insulation linings
- Wrapping of exhausts
- Flange jointing with openings for bolts (Aladder tapes)
- Radiant heat shields

Typical Physical Properties

Average density	600 - 800 kg/m ³
Colour	White
Basic Composition	Silica
Continuous Use Limit	550°C
Melting Point	840°C

Form: A3-059
Effective: 25081997.WVDS.mvo
Supersedes: SS.None
All Rights Reserved

Price schedule : K-3620/3630/3651

The information, recommendations and opinions set forth herein are offered solely for your consideration, inquiry and verification, and are not, in part or total, to be construed as constituting a warranty or representation for which we assume legal responsibility. Nothing contained herein is to be interpreted as authorization to practice a patented invention without a license.

Page 1 of 1

The Netherlands – Insulcon B.V.
Tel: +31(0)167-565750
Fax: +31(0)167-566263



Belgium – Keramab N.V.
Tel: +32(0)3 711 02 78
Fax: +32(0)3 711 08 56



Germany – Insulcon GmbH
Tel: +49(0)2162/ 24960-0
Fax: +49(0)2162/24960-29

