



TESNIT BAR-300



TECHNICAL DATA SHEET

Basis

Inorganic fibres, NBR, special reinforcement. Gasket material with strong reinforcement of wire mesh in twill weave, filled with gasket mixture of extremely high resistance.

General properties and application

High suitability for dynamically loaded joints at a very high temperature and pressure. Used in automotive and petrochemical industry, shipyards, exhaust systems.

Approvals

Germanischer Lloyd, CRS

Dimensions of standard sheets

Sheet size: 1000 x 1400 mm

Thickness: 0.7 mm, 1.2 mm, 1.4 mm

Tolerances: Thickness: < 1 mm ± 0.1 mm, ≥ 1 mm ± 10 %, Length: ± 50 mm, Width: ± 50

Surface treatment: Graphite.

Technical data

Typical values (thickness 2.0 mm)		
Compressibility	ASTM F 36/J	8 %
Recovery	ASTM F 36/J	40 %
Stress resistance	DIN 52913	
• 16h, 300°C, 50 MPa		40 MPa
• 16h, 175°C, 50 MPa		
Thickness increase	ASTM F 146	
• Oil IRM 903, 5h, 150°C		5 %
*Max. operating conditions		
Peak temperature		550°C / 1022°F
Continuous temperature		450°C / 842°F

* Temperature and pressure represent maximum values and should not be used simultaneously. They are given only for guidance, since they depend not only on the type of gasket material but also on the assembly conditions. Very important factors are: thickness of material, nature of service medium, type of flange, surface stress. Steam application requires special consideration.

In order to spread the most comprehensive knowledge of our products, our highly skilled group of experts organized in the technical-service department can assist you by solving practically any sealing problem. If you need our help, contact us.

DONIT TESNIT



DONIT TESNIT d.d.
Cesta komandanta Staneta 38
1215 MEDVODE, Slovenija
telefon: +386 (01) 582 32 00
fax: +386 (01) 582 32 06, 582 32 08
E-mail: info@donittesnit.si
http://www.donittesnit.si

This edition cancels all previous issues. Subject to change without notice.