

**FIBERFRAX DURABLANKET Z**

**The FIBERFRAX DURABLANKET family of lightweight needled blankets are manufactured from Fiberfrax refractory ceramic fibres and provide effective solutions to a wide spectrum of thermal management problems.**



Utilizing our proprietary high output blowing and spinning techniques these products offer superior insulating performance, flexibility and resilience. Fiberfrax Durablanket products are unaffected by most chemicals (except hydrofluoric & phosphoric acids and concentrated alkalis). Thermal and physical properties are retained after drying following wetting by oil, steam or water. Fiberfrax Durablanket products are completely inorganic, so there are no fumes when heating for the first time. Available in a variety of chemistry, density and thickness combinations, the Fiberfrax Durablanket range is one of the most versatile available to the market today.

FIBERFRAX DURABLANKET Z is a high temperature blanket made from spun zirconia stabilised ceramic fibre. It is a highly efficient insulator with extremely low shrinkage characteristics at elevated temperatures, low heat storage capacity and complete resistance to damage from thermal shock. Fiberfrax Durablanket Z is ideally suited to use in high temperature furnace lining systems.

**Typical applications**

- Investment casting mould wrappings
- Removable insulating blankets for field stress relieving welds
- Reusable insulation for steam and gas turbines
- Flexible high temperature pipe insulation
- High temperature kiln and furnace insulation
- Soaking pit seals
- Fire protection systems
- Expansion joint seals
- High temperature gasketing
- Glass furnace crown insulation
- Incineration equipment and stack linings
- Annealing cover seals
- High temperature filtration

**General characteristics**

FIBERFRAX DURABLANKET Z has these outstanding characteristics:

- High tensile strength
- Low shrinkage
- Excellent hot strength
- High resiliency
- Low thermal conductivity
- Low heat storage
- Resistance to thermal shock
- Good sound absorption
- High heat reflectance

Form: A1-052  
Effective: 18112008/ES/ka  
Supersedes: 0802006/ES/ka  
All Rights Reserved

Page 1 of 2

LD date: February 2006

The information, recommendations and opinions set forth herein are offered solely for your consideration, inquiry and verification, and are not, in part or total, to be construed as constituting a warranty or representation for which we assume legal responsibility. Nothing contained herein is to be interpreted as authorization to practice a patented invention without a license.

**The Netherlands – Insulcon B.V.**

Tel:+31(0)167-565750  
Fax:+31-(0)0167-566263

**INSULCON**  
LEADER IN HIGH TEMPERATURE SOLUTIONS

**Belgium – Keramab N.V.**

Tel:+32(0)37110278  
Fax:+32(0)37110856

**KERAMAB**  
LEADER IN HIGH TEMPERATURE SOLUTIONS

**Germany – Insulcon GmbH**

Tel:+49(0)2162/24960-0  
Fax:+49(0)2162-24960-29

**INSULCON**  
LEADER IN HIGH TEMPERATURE SOLUTIONS

Chemical Analysis (wt. %)	
SiO <sub>2</sub>	52,0 – 56,0
Al <sub>2</sub> O <sub>3</sub>	28,0 – 32,0
ZrO <sub>2</sub>	14,0 – 18,0
Alkalis	<0,25
Fe <sub>2</sub> O <sub>3</sub> + TiO <sub>2</sub>	<0,20

**Typical physical properties**

Colour	: White
Classification temperature	: 1400 °C
Melting point	: 1740 °C
Fibre diameter	: 3,25 microns (mean)
Specific heat at 1000°C	: 1035 J/kgK

	96 kg/m <sup>3</sup>	128 kg/m <sup>3</sup>	160 kg/m <sup>3</sup>
<b>Tensile strength</b> (kPa)	55	75	90
<b>Thermal conductivity data</b> (W/mK)			
Mean temperature :			
600°C	-	-	-
800°C	0,24	0,19	0,18
1000°C	0,34	0,27	0,25
1200°C	0,44	0,36	0,33

**Permanent linear shrinkage (24 hour soak)**

1200°C	: 2,1	%
1300°C	: 2,5	%
1400°C	: 2,6	%

Availability				
Thickness (mm)	Density (kg/m <sup>3</sup> )			Roll length (m)
	96	128	160	
13	✓	✓	✓	14,64
19	✓	✓	✓	10,0
25	✓	✓	✓	7,32
38	✓	✓	✓	5,0
50	✓	✓		3,66

Other thicknesses/sizes may be available on request subject to minimum order requirements.

Versions with aluminium foil and other coverings are available subject to order.

Standard roll: 610 mm

Form: A1-052  
Effective: 18112008/ES/ka  
Supersedes: 0802006/ES/ka  
All Rights Reserved

Page 2 of 2

LD date: February 2006

The information, recommendations and opinions set forth herein are offered solely for your consideration, inquiry and verification, and are not, in part or total, to be construed as constituting a warranty or representation for which we assume legal responsibility. Nothing contained herein is to be interpreted as authorization to practice a patented invention without a license.

**The Netherlands – Insulcon B.V.**

Tel:+31(0)167-565750  
Fax:+31-(0)0167-566263



**Belgium – Keramab N.V.**

Tel:+32(0)37110278  
Fax:+32(0)37110856



**Germany – Insulcon GmbH**

Tel:+49(0)2162/24960-0  
Fax:+49(0)2162-24960-29

